

**Product Description**

High Viscosity, UV Stabilized, Polycarbonate.  
Makropol DF grades have good diffusivity appropriate for LED lighting.

**General Considerations**

Resin ID (ISO 1043)	· PC	
Additive	· UV Resistant	· Diffuse
Processing	· Extrusion	
Color	· Haze	

<b>Physical</b>	<b>Dry</b>	<b>50%RH</b>	<b>Unit</b>	<b>Method</b>
Density	1200	--	kg/m <sup>3</sup>	ISO 1183
Mold Shrinkage				ISO 2577
Parallel	0,5	--	%	
Normal	0,7	--	%	
Water Absorption				ISO 62
Saturation (Water at 23°C)	--	0,3	%	
Equilibrium (23°C)	--	0,12	%	
Melt mass-flow rate 300 °C; 1.2 kg	20	--	g/10min	ISO 1133

<b>Mechanical</b>	<b>Dry</b>	<b>50%RH</b>	<b>Unit</b>	<b>Method</b>
Tensile Modulus (1mm/min)	--	2350	MPa	ISO 527-1,-2
Yield Stress (50 mm/min)	--	65	MPa	ISO 527-1,-2
Yield Strain (50 mm/min)	--	6,3	%	ISO 527-1,-2
Nominal Strain at Break				ISO 527-1,-2
Stress at Break (50 mm/min)	--	75	MPa	
Strain at Break (50 mm/min)	--	125	%	
Flexural Modulus (2 mm/min)	--	2350	MPa	ISO 178
Flexural Strength (2 mm/min)	--	96	MPa	ISO 178
Flexural Strain (2 mm/min)	--	7,2	%	ISO 178
Charpy Impact Strength				ISO 179-1eU
-30°C	--	Non-Break	kJ/m <sup>2</sup>	
23°C	--	Non-Break	kJ/m <sup>2</sup>	
Charpy Notched Impact Strength				ISO 179-1eA
-30°C	--	18	kJ/m <sup>2</sup>	
23°C	--	80	kJ/m <sup>2</sup>	
Izod Notched Impact Strength				ISO 180-A
-30°C	--	16	kJ/m <sup>2</sup>	
23°C	--	90	kJ/m <sup>2</sup>	

<b>Thermal</b>	<b>Value</b>	<b>Unit</b>	<b>Method</b>
Heat Deflection Temperature			ISO 75-1,-2
0,45 MPa	141	°C	
1,82 MPa	129	°C	
Thermal Conductivity	0,2	W/(m·K)	ISO 8302
Vicat Softening Temperature			ISO 306
50 N ; 50°C/h	149	°C	
50 N ; 120°C/h	150	°C	
Melting Point	280	°C	ISO 294
Coefficient of Linear Thermal Expansion			ISO 11359-1,-2
Parallel ; (23 to 55 °C)	0,65	10 -4 /K	
Transverse ; (23 to 55 °C)	0,65	10 -4 /K	

<b>Thermal</b>	<b>Value</b>	<b>Unit</b>	<b>Method</b>
Flammability			UL 94
0,75 mm	V-2	Class	
1,5 mm	V-2	Class	
2,8 mm	V-2	Class	
2,9 mm	HB	Class	
Glow Wire Test			IEC 60695-2-12
1,0 mm	850	°C	
1,5 mm	850	°C	
2,0 mm	850	°C	
3,0 mm	850	°C	

<b>Electrical</b>	<b>Dry</b>	<b>50%RH</b>	<b>Unit</b>	<b>Method</b>
Relative Permittivity				IEC 60250
100 Hz	--	3,1	--	
1 MHz	--	3,0	--	
Dissipation factor				IEC 60250
100 Hz	--	5	10 <sup>-4</sup>	
1 MHz	--	85	10 <sup>-4</sup>	
Surface Resistivity	--	1E+16	ohm	IEC 60093
Volume Resistivity	--	1E+14	ohm.m	IEC 60093
Electric Strength (1 mm)	--	33	kV/mm	IEC 60243-1

<b>Process</b>		<b>Unit</b>	<b>Method</b>
Molding Process Temperature	270 to 290	°C	--
Mold Temperature	70 to 90	°C	--
Drying	120/4	°C/Hours	--

Data contained in this Data Sheet have been obtained in laboratory and reflect the average number of batches produced. This information is current as of the date on which it was authorized to print this. The Petropol reserves the right to alter designs, specifications and information on its products at any time or discontinue them, regardless of any notice or statement without incurring liability of any kind.