

Product Description

Low Viscosity, UV Stabilized, Reinforced, Polycarbonate

General Considerations

Resin ID (ISO 1043)	· PC GF20	
Processing	· Injection Molding	· Extrusion
Color	· Natural	

- The information below is for informational purposes only and should not be adopted as specification limits.

Physical	Value	Unit	Method
Density / Specific Gravity	1,35 to 1,37	g/cm³	ASTM D 792/A
Mold Shrinkage	0,1 to 0,3	%	ASTM D 955
Water Absorption	0,16	%	ASTM D 570
Melt Mass-Flow Rate - 300°C; 1,2kg	15	g/10min	ASTM D 1238

Mechanical	Value	Unit	Method
Tensile Strength	75	MPa	ASTM D 638
Elongation at Break	5	%	ASTM D 638
Flexural Strength	130	MPa	ASTM D 790
Flexural Modulus	4900	MPa	ASTM D 790
Izod Notched Impact Strength 23°C	106	J/m	ASTM D 256

Thermal	Value	Unit	Method
Heat Deflection Temperature 1,82 Mpa	145	°C	ASTM D 648
Vicat Softening Temperature	160	°C	ASTM D 1525

Flammability	Value	Unit	Method
Flame Rating	HB	-	UL94

Process	Value	Unit	Method
Molding Process Temperature	280 to 300	°C	--
Mold Temperature	90 to 110	°C	--
Drying	110/6	°C/Hours	--

Os dados contidos neste Informativo Técnico foram obtidos em Laboratório e refletem a média de vários lotes produzidos. Estas informações encontram-se atualizadas até a data em que foi autorizada a impressão deste. A Petropol reserva-se o direito de alterar desenhos, especificações e informações de seus produtos a qualquer tempo ou descontinuará-los, independente de qualquer aviso ou comunicado sem incorrer em responsabilidade de qualquer espécie.

Data contained in this Data Sheet have been obtained in laboratory and reflect the average number of batches produced. This information is current as of the date on which it was authorized to print this. The Petropol reserves the right to alter designs, specifications and information on its products at any time or discontinue them, regardless of any notice or statement without incurring liability of any kind.