

Product Description

UV Stabilized, Flame Retardant, ABS

General Considerations

Resin ID (ISO 1043)	• ABS
Processing	• Injection Molding
Color	• Natural

- The information below is for informational purposes only and should not be adopted as specification limits.

Physical	Value	Unit	Method
Density / Specific Gravity	1,14	g/cm ³	ASTM D 792/A
Melt Flow Rate (220°C/10kg)	< 40	g/10min	ASTM D 955
Mold Shrinkage	0,4 to 0,8	%	ASTM D 1238

Mechanical	Value	Unit	Method
Tensile Strength	40	MPa	ASTM D 638
Flexural Strength	68	%	ASTM D 790
Flexural Modulus	2600	MPa	ASTM D 790
Izod Notched Impact Strength		J/m	ASTM D 256
23°C	>100		
Hardness, Rockwell R	100	R-Scale	ASTM D785

Thermal	Value	Unit	Method
Heat Deflection Temperature		°C	ASTM D 648
1,80 MPa	81		
Vicat Softening Temperature	105	°C	ASTM D1525

Flammability	Value	Unit	Method
Flammability (1,5mm)	V-0	--	UL-94

Process		Unit	Method
Molding Process Temperature	195 to 230	°C	--
Mold Temperature	50 to 70	°C	--
Drying	85 / 3	°C/Hours	--

Data contained in this Data Sheet have been obtained in laboratory and reflect the average number of batches produced. This information is current as of the date on which it was authorized to print this. The Petropol reserves the right to alter designs, specifications and information on its products at any time or discontinue them, regardless of any notice or statement without incurring liability of any kind.