

Product Description

30% Glass Reinforced, Polyamide 6

General Considerations

Resin ID (ISO 1043)	· PA6-GF30
Filler / Reinforcement	· Glass Fiber, 30% Filler by Weight
Processing	· Injection Molding
Color	· Black

- The information below is for information purposes only and should not be adopted as specification limits.

Physical	Value	Unit	Method
Density	1,37	g/cm ³	ASTM D 792/A
Mold Shrinkage	0,3 to 0,5	%	ASTM D 955
Water absorption	1	%	ASTM D 570

Mechanical	Value	Unit	Method
Tensile Stress	120	MPa	ASTM D 638
Elongation at break	3	%	ASTM D 638
Flexural Modulus	6900	MPa	ASTM D 790
Flexural Strength	200	MPa	ASTM D 790
Izod Notched Impact Strength 23°C	92	J/m	ASTM D 256

Thermal	Value	Unit	Method
Melting Point	210 to 225	°C	ISO 3146/A
Heat Deflection Temperature 1,82 MPa	200	°C	ASTM D 648
Vicat Softening Temperature	210	°C	ASTM D 1525

Process	Value	Unit	Method
Molding Process Temperature	230 to 250	°C	--
Mold Temperature	80 to 100	°C	--
Drying	80/4	°C/Hours	--

Data contained in this Data Sheet have been obtained in laboratory and reflect the average number of batches produced. This information is current as of the date on which it was authorized to print this. The Petropol reserves the right to alter designs, specifications and information on its products at any time or discontinue them, regardless of any notice or statement without incurring liability of any kind.