

Product Description

20% Glass Fiber, UV Resistant, ABS

General Considerations

Resin ID (ISO 1043)	· >ABS-GF20<	
Additive	· UV Resistant	
Processing	· Injection Molding	· Extrusion
Color	· Grey	

- The information below is for informational purposes only and should not be adopted as specification limits.

Physical	Value	Unit	Method
Density / Specific Gravity	1,17	g/cm ³	ASTM D 792/A
Mold Shrinkage	0,1 ~ 0,2	%	ASTM D 1238
Water Absorption	0,15	%	ASTM D 570

Mechanical	Value	Unit	Method
Tensile Strength	78	MPa	ASTM D 638
Elongation at Break	5	%	ASTM D 790
Flexural Strength	114	MPa	ASTM D 790
Flexural Modulus	5700	MPa	ASTM D 790
Izod Notched Impact Strength		J/m	ASTM D 256
23°C	60		
Izod Unnotched Impact Strength		J/m	ASTM D 256
23°C	248		
Hardness, Rockwell R	102	Scale R	ASTM D785

Thermal	Value	Unit	Method
Heat Deflection Temperature		°C	ASTM D 648
0,42 MPa	99		
1,80 MPa	93		

Flammability	Value	Unit	Method
Flammability (3,2mm)	HB	--	UL-94

Process	Value	Unit	Method
Molding Process Temperature	200 to 240	°C	--
Mold Temperature	60 to 80	°C	--
Drying	80/4	°C/Hours	--

Data contained in this Data Sheet have been obtained in laboratory and reflect the average number of batches produced. This information is current as of the date on which it was authorized to print this. The Petropol reserves the right to alter designs, specifications and information on its products at any time or discontinue them, regardless of any notice or statement without incurring liability of any kind.