

**Product Description**

30% Glass Fiber, Polyamide 66

**General Considerations**

Resin ID (ISO 1043)	· PA66 GF30
Filler / Reinforcement	· Glass Fiber, 30% Filler by Weight
Processing	· Injection Molding                      · Extrusion
Color	· Beige

**- The information below is for informational purposes only and should not be adopted as specification limits.**

<b>Physical</b>	<b>Value</b>	<b>Unit</b>	<b>Method</b>
Density / Specific Gravity	1,39	g/cm <sup>3</sup>	ASTM D 1238/A

<b>Mechanical</b>	<b>Value</b>	<b>Unit</b>	<b>Method</b>
Tensile Strength	156,5	MPa	ISO 527-1-2
Yield Strain	5	%	ISO 527-1-2
Flexural Strength	250	MPa	ISO 178
Flexural Modulus	7500	MPa	ISO 178
Izod Impact Strength		kJ/m <sup>2</sup>	ISO 180/1U
23°C	60		
Izod Notched Impact Strength		kJ/m <sup>2</sup>	ISO 180/1A
23°C	7,33		

<b>Thermal</b>	<b>Value</b>	<b>Unit</b>	<b>Method</b>
Melting Point	250 to 265	°C	ISO 3146-A
Heat Deflection Temperature		°C	ISO 75
1,82 MPa	240		
Flammability (2,0 mm)	HB	-	UL 94

<b>Process</b>	<b>Value</b>	<b>Unit</b>	<b>Method</b>
Molding Process Temperature	290 to 305	°C	--
Mold Temperature	70 to 120	°C	--
Drying	80/3 to 4	°C/Hours	--

Os dados contidos neste Informativo Técnico foram obtidos em Laboratório e refletem a média de vários lotes produzidos. Estas informações encontram-se atualizadas até a data em que foi autorizada a impressão deste. A Petropol reserva-se o direito de alterar desenhos, especificações e informações de seus produtos a qualquer tempo ou descontinuar-los, independente de qualquer aviso ou comunicado sem incorrer em responsabilidade de qualquer espécie.

Data contained in this Data Sheet have been obtained in laboratory and reflect the average number of batches produced. This information is current as of the date on which it was authorized to print this. The Petropol reserves the right to alter designs, specifications and information on its products at any time or discontinue them, regardless of any notice or statement without incurring liability of any kind.