

**Product Description**

30% Glass Fiber, Highly Lubrificated, Polyamide 66

**General Considerations**

Resin ID (ISO 1043)	· PA66-GF30	
Filler / Reinforcement	· Glass Fiber, 30% Filler by Weight	
Additive	· Highly Lubrificated	
Processing	· Injection Molding	· Extrusion
Color	· Black	

<b>Physical</b>	<b>Value</b>	<b>Unit</b>	<b>Method</b>
Density / Specific Gravity	1,50	g/cm <sup>3</sup>	ASTM D 792/A
Mold Shrinkage	0,3 to 0,7	%	ASTM D 955
Water Absorption		%	ASTM D 570
Equilibrium (23°C)	1,3		

<b>Mechanical</b>	<b>Value</b>	<b>Unit</b>	<b>Method</b>
Tensile Strength	120	MPa	ASTM D 638
Elongations at Break	2,0	%	ASTM D 638
Flexural Strength	190	MPa	ASTM D 790
Flexural Modulus	9700	MPa	ASTM D 790
Izod Notched Impact Strength		J/m	ASTM D 256
23°C	60		

<b>Thermal</b>	<b>Value</b>	<b>Unit</b>	<b>Method</b>
Melting Point	260	°C	--
Heat Deflection Temperature		°C	ISO 75-1-2
1,80 MPa	245		

<b>Process</b>		<b>Unit</b>	<b>Method</b>
Molding Process Temperature	270 to 290	°C	--
Mold Temperature	60 to 90	°C	--
Drying	90/4	°C/Hours	--

Data contained in this Data Sheet have been obtained in laboratory and reflect the average number of batches produced. This information is current as of the date on which it was authorized to print this. The Petropol reserves the right to alter designs, specifications and information on its products at any time or discontinue them, regardless of any notice or statement without incurring liability of any kind.