

Product Description

33% Glass Fiber, Polyamide 66

General Considerations

Resin ID (ISO 1043)	· PA66/6 GF33
Filler / Reinforcement	· Glass Fiber, 33% Filler by Weight
Processing	· Injection Molding
Color	· Natural

Physical	Value	Unit	Method
Density / Specific Gravity	1,37 to 1,41	g/cm ³	ASTM D 792

Mechanical	Value	Unit	Method
Yield Stress	180	MPa	ISO 527-1-2
Yield Strain	3	%	ISO 527-1-2
Flexural Strength	260	MPa	ISO 178
Flexural Modulus	8000	MPa	ISO 178
Izod Notched Impact Strength 23°C	15	kJ/m ²	ISO 180/1A

Thermal	Value	Unit	Method
Heat Deflection Temperature 1,82 Mpa	230	°C	ISO 75-1-2
Melting Temperature	242	°C	ISO 11357-3

Process		Unit	Method
Molding Process Temperature	250 to 280	°C	--
Mold Temperature	80 to 120	°C	--
Drying	80/4	°C/Hours	--

Data contained in this Data Sheet have been obtained in laboratory and reflect the average number of batches produced. This information is current as of the date on which it was authorized to print this. The Petropol reserves the right to alter designs, specifications and information on its products at any time or discontinue them, regardless of any notice or statement without incurring liability of any kind.