

Product Description

35% Glass Fiber, Polyamide 66

General Considerations

Resin ID (ISO 1043)	· PA66 GF35
Filler / Reinforcement	· Glass Fiber, 35% Filler by Weight
Processing	· Injection Molding
Color	· Natural

- The information below is for informational purposes only and should not be adopted as specification limits.

Physical	Value	Unit	Method
Density / Specific Gravity	1,41	g/cm ³	ASTM D 1238/A

Mechanical	Value	Unit	Method
Yield Strength	200	MPa	ISO 527-1-2
Yield Strain	3	%	ISO 527-1-2
Flexural Strength	300	MPa	ISO 178
Izod Notched Impact Strength 23°C	17	kJ/m ²	ISO 180/1A

Thermal	Value	Unit	Method
Melting Point	262	°C	ISO 3146-A
Heat Deflection Temperature 1,82 MPa	252	°C	ISO 75

Process	Value	Unit	Method
Molding Process Temperature	285 to 305	°C	--
Mold Temperature	70 to 120	°C	--
Drying	80/3 to 4	°C/Hours	--

Data contained in this Data Sheet have been obtained in laboratory and reflect the average number of batches produced. This information is current as of the date on which it was authorized to print this. The Petropol reserves the right to alter designs, specifications and information on its products at any time or discontinue them, regardless of any notice or statement without incurring liability of any kind.