

**Product Description**

UV Resistant, Lubrificated, ABS

**General Considerations**

Resin ID (ISO 1043)	· ABS
Additive	· UV Stabilizer
Processing	· Injection Molding
Color	· Natural

- The information below is for informational purposes only and should not be adopted as specification limits.

Physical	Value	Unit	Method
Density / Specific Gravity	1,04	g/cm <sup>3</sup>	ASTM D 792/A
Melt Flow Rate (220°C/10kg)	21	g/10min	ASTM D 1238/A

Mechanical	Value	Unit	Method
Tensile Strength	50	MPa	ASTM D 638
Elongation at break	10	%	ASTM D 638
Flexural Strength	80	MPa	ASTM D 790
Flexural Modulus	2800	MPa	ASTM D 790
Izod Notched Impact Strength 23°C	230	J/m	ASTM D 256

Thermal	Value	Unit	Method
Heat Deflection Temperature 1,80 Mpa	83	°C	ASTM D 648
Vicat Softening Temperature	94	°C	ASTM D 1525

Flammability	Value	Unit	Method
Flammability (3,2mm)	HB	--	UL-94

Process	Value	Unit	Method
Molding Process Temperature	190 to 230	°C	--
Mold Temperature	40 to 70	°C	--
Drying	80/2 to 4	°C/Hours	--

Data contained in this Data Sheet have been obtained in laboratory and reflect the average number of batches produced. This information is current as of the date on which it was authorized to print this. The Petropol reserves the right to alter designs, specifications and information on its products at any time or discontinue them, regardless of any notice or statement without incurring liability of any kind.