

**Product Description**

Heat Stabilized, High Impact, Polyamide 66

**General Considerations**

Resin ID (ISO 1043)	· PA66	
Additive	· High Impact	
Processing	· Injection Molding	· Extrusion
Color	· Natural	

<b>Physical</b>	<b>Value</b>	<b>Unit</b>	<b>Method</b>
Density / Specific Gravity	1,07 to 1,09	g/cm <sup>3</sup>	ASTM D 792/A

<b>Mechanical</b>	<b>DAM</b>	<b>50%RH</b>	<b>Unit</b>	<b>Method</b>
Yield Stress	50	40	MPa	ISO 527
Yield Strain	50	-	%	ISO 527
Tensile Modulus	1950	900	MPa	ISO 527
Flexural Modulus	1750	650	MPa	ISO 178
Izod Notched Impact Strength 23°C	80	100	kJ/m <sup>2</sup>	ISO 180/1A

<b>Thermal</b>	<b>Value</b>	<b>Unit</b>	<b>Method</b>
Heat Deflection Temperature 1,82 MPa	60	°C	ISO 75-1-2
0,45 MPa	180		
Melting Point	260	°C	--

<b>Flammability</b>	<b>Value</b>	<b>Unit</b>	<b>Method</b>
Flame Rating	HB	-	UL94

<b>Process</b>	<b>Value</b>	<b>Unit</b>	<b>Method</b>
Molding Process Temperature	270 to 290	°C	--
Mold Temperature	60 to 80	°C	--
Drying	80/5	°C/Hours	--

Data contained in this Data Sheet have been obtained in laboratory and reflect the average number of batches produced. This information is current as of the date on which it was authorized to print this. The Petropol reserves the right to alter designs, specifications and information on its products at any time or discontinue them, regardless of any notice or statement without incurring liability of any kind.