

Product Description

Lubricated, Polyamide 66/6

General Considerations

Resin ID (ISO 1043)	· PA66/6
Additive	· Lubricated
Processing	· Injection Molding
Color	· Natural

- The information below is for informational purposes only and should not be adopted as specification limits.

Physical	Value	Unit	Method
Density / Specific Gravity	1,14	g/cm ³	ASTM D 792/A

Mechanical	Value	Unit	Method
Tensile Strength	60	MPa	ASTM D 638
Elongation at Break	35	%	ASTM D 638
Flexural Strength	100	MPa	ASTM D 790
Flexural Modulus	2950	MPa	ASTM D 790
Izod Notched Impact Strength 23°C	50	J/m	ASTM D 256

Thermal	Value	Unit	Method
Melting Point	245	°C	ISO 3146/A

Process		Unit	Method
Molding Process Temperature	260 to 280	°C	--
Mold Temperature	70 to 90	°C	--
Drying	80/2 to 4	°C/Hours	--

Data contained in this Data Sheet have been obtained in laboratory and reflect the average number of batches produced. This information is current as of the date on which it was authorized to print this. The Petropol reserves the right to alter designs, specifications and information on its products at any time or discontinue them, regardless of any notice or statement without incurring liability of any kind.