

Product Description

20% Glass Reinforced, UV Stabilized, Polyamide 6

General Considerations

Resin ID (ISO 1043)	· PA6-GF20
Filler / Reinforcement	· Glass Fiber, 20% Filler by Weight
Processing	· Injection Molding · Extrusion
Color	· Black

- The information below is for information purposes only and should not be adopted as specification limits.

Physical	Value	Unit	Method
Density	1,26	g/cm ³	ASTM D 792/A
Mold Shrinkage	0,3 to 0,5	%	ASTM D 955
Water absorption	1	%	ASTM D 570

Mechanical	Value	Unit	Method
Tensile Stress	140	MPa	ISO 527-1-2
Elongation at break	5	%	ASTM D 638
Flexural Modulus	9500	MPa	ASTM D 790
Flexural Strength	205	MPa	ASTM D 790
Izod Notched Impact Strength 23°C	8	kJ/m ²	ISO 180-1/A

Thermal	Value	Unit	Method
Melting Point	210 to 225	°C	ISO 3146/A

Process	Value	Unit	Method
Molding Process Temperature	230 to 250	°C	--
Mold Temperature	80 to 100	°C	--
Drying	80/4	°C/Hours	--

Data contained in this Data Sheet have been obtained in laboratory and reflect the average number of batches produced. This information is current as of the date on which it was authorized to print this. The Petropol reserves the right to alter designs, specifications and information on its products at any time or discontinue them, regardless of any notice or statement without incurring liability of any kind.